



RTV133

Description

RTV133 black, one-component, ready-to-use, silicone rubber adhesive sealant is recommended for evaluation in applications in the electronic, aerospace, appliance, transportation and other industries where resistance to burning of the finished product is a significant design consideration. On exposure to moisture in the air at room temperature, this adhesive sealant cures to a tough, durable, resilient silicone rubber. It utilizes an atmospheric moisture cure system, which releases an alcohol vapor from the sealant surface during cure. RTV133 sealant offers low odor cure with no unpleasant smell or pungent cure by-products. It is, however, somewhat slower curing both in tack-free time and cure-through time than atmospheric moisture cure silicone adhesive sealants which give off acetic acid vapors as a cure by-product.

Because RTV133 sealant has a paste-like consistency and will flow only with external pressure, it is suitable for use on horizontal, vertical and overhead surfaces in thicknesses to 6mm (¼ in.). It has sufficient uncured body to adhere to small objects while cure is taking place. For applications requiring sealant thickness greater than 6mm (¼ in.), Momentive Performance Materials one-component, addition cure or two-component silicone rubber compounds with similar properties are available.

Key Features and Benefits

- One-component product
- Thixotropic paste consistency
- Low flammability-has a UL rating of V-0 or V-1 using UL-94 test
- Capability to cure at room temperature and ambient humidity conditions
- Self adhesion properties
- Resistance to high temperatures
- Low temperature flexibility
- Excellent weatherability and ozone and chemical resistance
- Excellent electrical insulation properties
- Non-halogen flame re

Typical Physical Properties

Typical Uncured Properties	RTV133
Color	black
Consistency	soft, spreadable paste
Specific Gravity	1.23
Application Rate, gm/min.	650
Tack-Free Time, hours	1
Typical Cured Properties	RTV133
Mechanical:	
Hardness, Shore A	45
Tensile Strength, kg/cm ² (lb/in ²)	46 (650)
Elongation, %	250

Shear Strength, kg/cm ² (1b/in ²) ⁽¹⁾	12 (170)
Flammability (UL94), 3.38mm (1/8 in.) thick ⁽²⁾	V-0
Electrical: ⁽³⁾	
Dielectric Strength, kv/mm(v/mil)	20 (500)
Dielectric Constant @ 100 Hz	2.8
Dissipation Factor @ 100 Hz	0.001
Volume Resistivity, ohm-cm	3x10 ¹⁵
Thermal: ⁽³⁾	
Brittle Point, °C (°F)	< -60 (< -75)
Thermal Conductivity, W/mK(cal/sec, cm ² , °C/cm)	0.21(0.0005)
Coefficient of Expansion, cm/cm,°C (in/in, °F)	< 27x10 ⁻⁵ (< 15x10 ⁻⁵)

(1) At 100% cohesive failure. (2) This numerical flame spread rating is not intended to reflect hazards presented by this or any other material under actual fire conditions. (3) Information is provided for customer convenience only. Properties are not tested on a routine basis.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

RTV133 sealant is manufactured and sold for industrial use only.

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at www.momentive.com or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations

Applications

RTV133 silicone rubber adhesive sealant should be considered for industrial applications where reduced flammability characteristics of the finished product are important.

Typical applications include coatings for electronic and integrated circuits and semi-conductors and connections on electronic parts assemblies. Because of the low odor of its cure by-product, RTV133 sealant is also suitable for mechanical applications in confined work areas where the odor of other moisture vapor cure sealants might be objectionable.

Surface Preparation

RTV133 silicone rubber adhesive sealant will bond to many clean surfaces without the aid of a primer. These surfaces normally include many metals, glass, ceramic, silicone rubber and some rigid plastics. The adhesive sealant product will also produce fair bonds to some organic rubber and flexible plastics not containing fugitive plasticizers (which migrate to the surface impairing adhesion). An evaluation should be made to determine bond strength for each specific application. For difficult-to-bond substrates, use of a primer is suggested. SS4004, SS4044 and SS4179 primers are recommended for use with this sealant. Complete information and usage instructions for these primer products are contained in a separate product data sheet.

Where adhesion is required, surfaces should be thoroughly cleaned with a suitable solvent to remove dirt, oil and grease. The surface should be dry before applying the adhesive sealant. When solvents are used, proper safety precautions must be observed.

Cure Time Cycle

RTV133 adhesive sealant may be applied directly to a clean or primed substrate. The adhesive sealant begins to cure on exposure to moisture in the air at room temperature. Where broad surfaces are to be mated, the sealant should be applied in a thin, less than 6mm (¼ in.) diameter, bead or ribbon around the edge of the surface to be bonded.

The cure process begins with the formation of a skin on the exposed surface of the sealant and progresses inward through the material. At 25°C (77°F) and 50% relative humidity, this product will form a surface skin which is tack-free to the touch in 3 to 5 hours. Once the tack-free skin has begun to form, further tooling of the adhesive sealant is not advisable.

Higher temperatures and high humidity will accelerate the cure process low temperatures and low humidity will slow the cure rate.

As the adhesive sealant cures, alcohol vapors are released from the sealant surface. This by-product of cure has a slight, but non-objectionable odor which will diminish as the cure progresses.

A 3mm (1/8 in.) section of adhesive sealant will cure through in approximately 48 hours at 25°C (77°F) and 50% relative humidity. Since cure time increases with thickness, use of RTV133 sealant should be limited to section thicknesses of 6mm (¼ in.) or less.

Bond Strength Development

In addition to the effects of temperature and relative humidity, development of maximum bond strength will depend on joint configuration, degree of confinement, sealant thickness and substrate porosity. Normally, sufficient bond strength will develop in 24 to 48 hours to permit handling of parts. Minimum stress should be applied to the adhesive bond until full adhesive strength is developed. Always allow maximum cure time available for best results.

PACKAGING AND DISPENSING

RTV133 adhesive sealant is supplied ready-to-use in plastic caulking cartridges and in bulk containers.

The sealant may be dispensed from caulking cartridges by using simple mechanical caulking guns or air-operated guns. Air-operated guns will allow greater control and application speed. Cartridges are easy to use, can be put into production quickly and require minimum capital investment.

Note: Do not exceed 45 psig when used in air-powered caulking guns.

Bulk containers require a larger initial investment in dispensing equipment, but offer the most economical packaging for volume production. Bulk dispensing systems are air-operated extrusion pumps coupled to hand or automated dispensing units. Pumps which are specifically designed for pumping one-component RTV silicone rubber have TEFLON® seals, packings and TEFLON® lined hoses to prevent moisture permeation and pump cure problems.

CLEAN UP AND REMOVAL

Before cure, solvent systems such as naphtha or methyl ethyl ketone (MEK) are effective.

After cure, selected chemical strippers which will remove the silicone rubber are available from other manufacturers. Specific product information may be obtained on request.

TEFLON is a Registered Trademark of DuPont.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Specifications

FLAMMABILITY

Underwriters Laboratories Inc., Standard 94 describes a vertical burning test to be performed under laboratory conditions. In this test specimens are placed in the flame of a laboratory burner, and the ability of the substance to sustain a flame over a specified period of time upon removal of the source of the flame is determined. When tested by this procedure in the Momentive Performance Materials laboratory, RTV133 sealant has exhibited burning characteristics for a classification of 94V-O(2). Potential users of RTV133 sealant should refer to UL-94 for details of the test and the classification limits.

Each potential user should determine for himself/herself whether this test procedure is meaningful for his particular application and should run independent tests to determine whether RTV133 sealant is suitable for such particular application.

The above test, claims, representations and descriptions regarding the flammability of the product described are based on a standard small scale laboratory test and as such are not reliable for determining, evaluating, predicting or describing the flammability or burning characteristics of this product under actual fire conditions, whether this product is used alone or in combination with other products.

2) Underwriters Laboratories, Inc. Standard 94 describes a vertical burning test to be performed under laboratory conditions. In this test, specimens are placed in the flame of a laboratory burner, and the ability of the substance to sustain a flame over a specified period of time, upon removal of the source of the flame, is determined. The claims, representation, and descriptions regarding the flammability of the product described are based on a standard, small-scale laboratory test and as such are not reliable for determining, evaluating, predicting, or describing the flammability or burning characteristics of the product under actual fire conditions, whether the product is used alone or in combination with other products. Each potential user should determine for himself/herself whether a particular test procedure is meaningful for a particular application and should run independent tests to determine whether the product is suitable for a particular application.

UL STATUS

RTV133 adhesive sealant is recognized by Underwriters Laboratories, Inc. under the Component Recognition Program (UL File No. E36952).

FDA STATUS

This product is not suitable for FDA regulated applications.

PATENTS

The product RTV133 is within the scope of Patent 4,102,852.

Contact Information

For product prices, availability, or order placement, contact our customer service by visiting momentive.com/ContactSilicones.

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER

The information provided herein was believed by Momentive Performance Materials Inc. (collectively with its subsidiaries, "Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user's intended application or use. All products supplied by Momentive are subject to Momentive's standard terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE**, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.