

# **Technical Data Sheet**



# TSE3032

## **TSE3032**

# **Description**

TSE3032 is a two-component, low viscosity, transparent silicone rubber designed for electrical and electronic potting. The product cures at room temperature or by low temperature heat to transparent elastic rubber with the addition of curing agents.

# **Key Features and Benefits**

- Low viscosity permits excellent potting
- Transparent appearance
- Cure rate can be accelerated by heat
- No reactive by-products: no concerns regarding corrosion
- Excellent resistance to temperature extremes

# **Typical Physical Properties**

| UNCURED PROPERTIES                               |                            | TSE3032(A)                                  | TSE3032(B) |
|--|----------------------------|---|------------|
| Appearance                                       |                            | Transparent liquid                          |            |
| Viscosity (23°C)                                 | Pa•s {P}                   | 4.2 {42}                                    | 0.7 {7}    |
| Mixing Ratio by Weight                           |                            | 100:10                                      |            |
| Viscosity after Mixing (23°C)                    | Pa•s {P}                   | 4.0 {40}                                    |            |
| Work Life* (23°C) h                              |                            | 4   |            |
| CURED PROPERTIES (1h @ 100                       | °C)                        |   |            |
| Appearance                                       |                            | Transparent elastic rubber                  |            |
| Density (23°C)                                   | g/cm <sup>3</sup>          | 1.02  |            |
| Hardness (Type A)                                |                            | 35  |            |
| Tensile Strength                                 | MPa {kgf/cm <sup>2</sup> } | 4.5 {46}                                    |            |
| Elongation                                       | %                          | 210   |            |
| Refractive Index (n <sub>D</sub> <sup>25</sup> ) |                            | 1.406                                       |            |
| Linear Expansion*                                | 1/K                        | 2.3x10 <sup>-4</sup>                        |            |
| Thermal Conductivity*                            | W/m•K                      | 0.17  |            |
| Volume Resistivity                               | MΩ •m {Ω·•cm}              | 2.0x10 <sup>7</sup> {2.0x10 <sup>15</sup> } |            |
| Dielectric Strength                              | kV/mm                      | 21  |            |
| Dielectric Constant (60Hz)                       |                            | 2.8   |            |
| Dissipation Factor (60Hz)                        |                            | 0.001                                       |            |

\* In-house test methodTypical property data values should not be used as specifications.

# **Potential Applications**

- Potting of electronics parts requiring resistance to temperature extremes
- Potting of high voltage parts
- Moisture-proof coating of electronic circuit boards
- Potting of various modules

#### **Curing Properties**

| Temperature°C | Cure Timeh |  |
|---------------|------------|--|
| 70            | 4          |  |
| 100           | 1          |  |
| 150           | 0.25       |  |

#### **Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

## **Product Safety, Handling and Storage**

- Store in a cool and dry place out of direct sunlight.
- Keep out of the reach of children.

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at <a href="https://www.momentive.com">www.momentive.com</a> or, upon request, from any Momentive Performance Materials (MPM) representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

# **Processing Recommendations**

- All parts should be as clean and dry as possible prior to application.
- Materials such as water, sulfur, nitrogen compounds, organic metallic salts, phosphorus compounds, etc. contained in the surface of the substrate can inhibit curing. A sample patch should always be conducted before proceeding to determine compatibility.
- TSE3032(B) generates flammable gas on contact with acids, bases or oxidizing materials.
- Wear eye protection and protective gloves at all times when working with this product.
- Use the product in a well-ventilated area.

#### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

# **Packaging**

- TSE3032(A): 1kg can available in cases of 10, 15kg pail available
- TSE3032(B): 100g bottle available in cases of 20, 500g bottle available in cases of 10, 15kag can available

#### Contact Information

 $For product \ prices, \ availability, \ or \ order \ placement, \ contact \ our \ customer \ service \ by \ visiting \ \underline{momentive.com/ContactSilicones}.$ 

For literature and technical assistance, visit our website at: www.momentive.com

#### DISCLAIMER

The information provided herein was believed by Momentive Performance Materials Inc. (collectively with its subsidiaries, "Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user's intended application or use. All products supplied by Momentive are subject to Momentive's standard terms and conditions of sale. MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.