



TSE3250

TSE3250

Description

TSE3250 is a one-component heat curable, low viscosity silicone adhesive designed for potting and encapsulation. This product adheres to many substrates without a primer and cures at elevated temperatures. This product has a very long working time at room temperature.

Key Features and Benefits

- Ready to use-one component product
- Heat accelerated cure
- Low viscosity-easy pourable
- Primerless adhesion to many types of substrates
- No cure by-products, low linear shrinkage
- Non-corrosive to metals and sensitive substrates
- Outstanding performance over a wide temperature range

Typical Physical Properties

Uncured Properties		TSE3250
Color		Transparent
Viscosity @23°C	mPa-s	1300
Specific Gravity @23°C	g/cm ³	0.97
Cured Properties (cured 1 hour at 150°C)		
Hardness	Shore A	12
Adhesive strength (Al to Al)	MPa	0.1
Dielectric Strength	kV/mm	21
Dielectric Constant		2.8
Dissipation Factor		0.001
Volume Resistivity	ohm-cm	2 x 10 ¹⁵
Thermal expansion Coefficient	1/K	2.5x10 ⁻⁴
Thermal Conductivity	W/m.°K	0.17

Potential Applications

- Coating of hybrid IC's, printed circuit boards, etc
- Dip and spray coating and encapsulation of electronic devices

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

CAUTION

TSE3250 silicone adhesive can generate flammable hydrogen gas upon contact with acidic, basic, or oxidizing materials. Such contact should be avoided.

The shelf life will be indicated by the 'use before date' on the associated documents with a minimum of 3 months when stored in the original unopened containers between 2° and 10 °C

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at www.momentive.com or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations**Compatibility**

TSE3250 silicone adhesive cures in contact with most clean, dry surfaces. However, certain materials, such as butyl and chlorinated rubber, sulfurcontaining materials, amines, and certain metal soap cured RTV silicone rubber compounds can cause cure inhibition. Cure inhibition is characterized by a gummy appearance of the TSE3250 silicone adhesive at the interface between the adhesive and the substrate to be bonded. It is recommended that a sample patch test be performed with the TSE3250 silicone adhesive to determine substrate compatibility.

Surface Preparation

The adhesive performance of any polymer system is highly dependent upon proper surface preparation. In order to maximize the adhesion of TSE3250 silicone adhesive and minimize the potential for cure inhibition, all parts should be as clean and dry as possible prior to the application of the adhesive.

Curing

TSE3250 silicone adhesive requires elevated temperatures in order to achieve full cure. Typical cure times and temperatures are as follows:

Temperature	TSE3250
100°C	4 hours
120°C	2 hours
150°C	1 hour

The actual cure time is affected by such things as cross-sectional thickness of the TSE3250 silicone adhesive, heat capacity of the overall assembly and efficiency and type of oven used (i.e. convection, infrared)

Adhesion capability

Suitable substrates
Metals: Aluminium, Copper, Ni plate; Stainless steel
Plastics: PPS, PBT, Epoxy resin, Polyester, Phenolic resin
Rubbers: Heat cured silicone rubber
Inorganics: Glass, Ceramics

Not suitable substrates
Plastics: PP, PE, Fluorocarbon resin
Rubbers: Sulphur vulcanized rubbers, Fluorocarbon rubber

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Availability

TSE3250 is available in 1kg cans and 15 kg pails.

Contact Information

For product prices, availability, or order placement, contact our customer service by visiting momentive.com/ContactSilicones.

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER

The information provided herein was believed by Momentive Performance Materials Inc. (collectively with its subsidiaries, "Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user's intended application or use. All products supplied by Momentive are subject to Momentive's standard terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE**, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.