



# SiTRUST\* TSE3661

## Description

SiTRUST TSE3661 is a two-component condensation cure silicone rubber designed for electric potting. SiTRUST TSE3661 cures at room temperature to form an elastic rubber and adheres to various types of materials such as metal, plastics, glass and ceramics without the use of primers.

## Key Features and Benefits

- Low viscosity allows for excellent flowability
- Fast Cure
- Excellent deep section cure
- Excellent adhesive properties : primerless adhesion to many types of substrates
- No cure inhibition
- Flame retardant: UL94HB recognized (File No: E56745)

## Typical Physical Properties


(JIS K 6249)		
Uncured Properties (23°C, 50%RH)	SiTRUST TSE3661(A)	SiTRUST TSE3661(C)
Appearance	White	Blue-Green
Specific Gravity	1.20	1.04
Viscosity Pa*s	4.0	0.01
Mixing Ratio by Weight	100:3	
Viscosity after Mixing Pa*s	3.5	
Pot Life, h	0.1	
Tack Free Time, min	20	
Cured Properties (3 days @ 23°C, 50%RH)		
Appearance	Elastic rubber, Blue-Green	
Density g/cm <sup>3</sup>	1.20	
Hardness (Type A)	30	
Tensile Strength, MPa	1.1	
Elongation, %	120	
Adhesive Strength (GL lap share) MPa	0.8	

Volume Resistivity, $\Omega \cdot m$	$1.0 \times 10^{15}$
Dielectric Strength, kV/mm	20
Dielectric Constant (60Hz)	3.2
Dissipation Factor (60Hz)	0.02
Thermal Conductivity <sup>(1)</sup> W/m•K	0.27


1) In-house test method Typical property data values should not be used as specifications.

### Potential Applications

- Potting of electric and communications parts
- Moisture proof sealing of meters
- Moisture proof coating of electric circuit boards



### Cure Property: Hardness (23°C, 50%RH)



## Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

## Product Safety, Handling and Storage

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

## Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

## Contact Information

For product prices, availability, or order placement, contact our customer service by visiting [momentive.com/ContactSilicones](http://momentive.com/ContactSilicones).

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

## DISCLAIMER

The information provided herein was believed by Momentive Performance Materials Inc. (collectively with its subsidiaries, "Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user's intended application or use. All products supplied by Momentive are subject to Momentive's standard terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE**, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**